



LABORATORY:- MOXLEY INDUSTRIAL CENTRE, WESTERN WAY, **ADDRESS** WEDNESBURY, WEST MIDLANDS, WS10 7BG

TEL: 0121 505 4050 www.rotechlabs.co.uk FAX: 0121 505 1115 info@rotechlabs.co.uk Report

Our Ref:	GBW	Number	96215	Issue	1	Date	19/04/2012	Page	1	of_	1
A /C NI	14114										

A/C No: M114

Tested For:-

T I MIDWOOD & COMPANY LIMITED

Green Lane Wardle Nantwich Cheshire CW5 6BJ

SALT SPRAY TESTING OF TIMCO ZINC DRYWALL SCREW SAMPLES

INTRODUCTION

The finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description:

7 off. Timco Zinc Drywall Screw Samples

Finish:

Zinc Plated / Steel

Specification:

Salt Spray Test in accordance with ASTM.B117-09

Test Duration:

60 Hours Exposure Peter Owen

Submitted By:

Verbal

Customer's Order No: Sample Receipt Date:

03/04/2012

RESULTS

Salt Spray Test (ASTM B117-09 / BS EN ISO 9227:2006 / DIN.50.021-SS)

The screw samples were exposed to a neutral 5% Salt Spray for a test period of 60 hours.

The screw samples showed no evidence of red ferrous corrosion after 60 hours exposure.

CONCLUSION

The finish applied to the Timco Zinc Drywall Screw Samples tested, withstood 60 hours Salt Spray Test without the formation of red ferrous corrosion.

REPORT COMPILED BY

REPORT APPROVED BY

G B Withers Corrosion Science

G B Withers Corrosion Science

Technician

Technician

TESTS MARKED "NOT UKAS ACCREDITED" INTHIS REPORT/CERTIFICATE ARE NOT INCLUDED IN THE UKAS ACCREDITATION SCHEDULE FOR OUR LABORATORY TESTS MARKED "SC" HAVE BEEN SUBCONTRACTED.

OPINIONS AND INTERPRETATIONS EXPRESSED HEREN ARE OUTSIDE THE SCOPE OF UKAS ACCREDITATION.

THIS TIST REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL OF THE LABORATORY.

RESULTS IN THIS REPORT RELATE ONLY TO THE ITEMS TISTED.