

THE FOLLOWING SALT SPRAY TEST REPORT APPLIES TO ALL TIMco WINDOW SCREWS  
MANUFACTURED FROM 410 MARTENSITIC STAINLESS STEEL & SILVER RUSPERT FINISH.

# ROTECH

LABORATORIES

MOXLEY INDUSTRIAL CENTRE  
WESTERN WAY  
WEDNESBURY  
WEST MIDLANDS  
WS10 7BG  
TEL: 0121 505 4050  
FAX: 0121 505 1115  
[www.rotechlabs.co.uk](http://www.rotechlabs.co.uk)  
[info@rotechlabs.co.uk](mailto:info@rotechlabs.co.uk)



0366

## Test Report

Our Ref: GBW      Number 162554-3      Issue 1      Date 19/12/2016      Page 1 of 2

A/C No: M114

Tested For:-

T I MIDWOOD & COMPANY LIMITED  
Green Lane  
Wardle  
Nantwich  
Cheshire  
CW5 6BJ

### SALT SPRAY TESTING OF TIMCO 3.9 x 25mm WINDOW SCREW SAMPLES

#### INTRODUCTION

The finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

#### RELEVANT INFORMATION

Description:	20 off. Timco 3.9 x 25mm S/Drill PVC CSK-S/S Screw Samples
Finish:	Martensitic Stainless Steel & Silver Ruspert
TIMco Code:	123 SS
Batch No.	5055017529537
Specification:	Salt Spray Test in accordance with BS EN ISO 9227:2012
Test Duration:	504 Hours Salt Spray Exposure
Submitted By:	Cris Tonks
Customer's Order No:	5277CT
Sample Receipt Date:	24/11/2016

#### RESULTS

##### Salt Spray Test (BS EN ISO 9227:2012)

The samples were exposed to a neutral 5% Salt Spray, for a test period of 96 hours.

Examination after every 24 hours revealed the following observations:-

##### 24 – 504 Hours

The samples showed no evidence of red ferrous corrosion.

REPORT  
COMPILED BY



G B Withers

Corrosion Science Technician

REPORT  
APPROVED BY



G B Withers

Corrosion Science Technician

TESTS MARKED "NOT UKAS ACCREDITED" IN THIS REPORT/CERTIFICATE ARE NOT INCLUDED IN THE UKAS ACCREDITATION SCHEDULE FOR OUR LABORATORY.  
TESTS MARKED "SC" HAVE BEEN SUBCONTRACTED.  
RESULTS IN THIS REPORT RELATE ONLY TO THE ITEMS TESTED  
OPINIONS AND INTERPRETATIONS EXPRESSED HEREIN ARE OUTSIDE THE SCOPE OF UKAS ACCREDITATION.  
THIS TEST REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL OF THE LABORATORY